

## STUCCO SL20

### Technical Sheet

<b><u>NAME:</u></b>	<b>STUCCO SL20</b>
<b><u>TYPE:</u></b>	Stucco acting as a filler for indoor
<b><u>USE</u></b>	To use for grout lines between tiles or in case of cracks or holes, before applying METEORE 12.
<b><u>TECHNICAL DATA:</u></b>	<b>specific weight:</b> 1.650 ± 30 gr/LT. at 25°C <b>viscosity:</b> 60000 cps <b>yield:</b> = = = <b>aesthetic effect:</b> = = = <b>colours:</b> white <b>packaging:</b> LT. 0,250-0,500
<b><u>DRYING TIME:</u></b>	<b>on the surface:</b> = = = <b>overpainting</b> 4 hours at 20 °c <b>below the surface:</b> = = =
<b><u>CARACTERISTICS AND RESISTANCE:</u></b>	high toxtotropy for filling the joints among tiles and surface leveling
<b><u>PREPARATION OF THE SURFACE:</u></b>	
<b><u>PREPARATION OF THE PRODUCT:</u></b>	<b>dilution:</b> ready to use <b>system:</b> spatula <b>number of coatings:</b> 1
<b><u>APPLICATION:</u></b>	For grout lines between tiles or in case of cracks or holes, use the STUCCO SL20 filler before applying METEORE 12. <b>temperature of application</b> superior to + 5°C and inferior to +30°C <b>storage:</b> make sure that the can is tightly closed, even after use, and store at a temperature between +10°C and +30°C. <b>stability:</b> approximately 1 year, if the containers are well sealed and never opened

### **NOTE:**

Mix carefully before use. Wash tools using water and soap after use with ethyl alcohol

Technical Sheet n° SC 00270 issued by the Control Quality Department:  
Edition n°1 January 2018