



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC 00116

FINISH V 16

Technical data

NAME:

FINISH V 16

GROUP:

transpiring acrylic protective

UTILISATION:

transparent paint for indoor and outdoor. Formulated and tested for the protection of Artecó'1 and Polistof. It acts as a primer as applied before Magic Light Finitura K 100 application

CHARACTERISTICS:

specific weight: 1000 ± 30 gr/l at 20°C

viscosity: low viscosity

yield: 25 m²/LT. for Artecó'1 (not diluted)
40-50 m²/LT for Artecó'1 (diluted at 100% with water)
12 m²/LT for Polistof (not diluted)
15-20 m²/LT for Magic Light Finitura K 100
(it may vary according to the roughness, porosity and surface absorption and to the method of application)

appearance: mat

colour: transparent

packing: cans of LT. 0,250 l. - LT.1

DRYING TIME:

on surface: 30 min. at 20°C

2nd coat: 2 hrs at 20°C

in depth: 24 hrs at 20°C

CHARACTERISTICS AND RESISTANCE:

FOR ARTECO'1 If it is applied on interior walls, tables, chairs and other furniture Finish V 16 protects the surface decorated with Artecó'1 making it resistant to washing with water, to bumps and abrasion. Moreover it prevents whitening and efflorescence of lime in Artecó'1 when application is outdoor.

FOR POLISTOF: if it is applied on wood, iron, glass and light alloys surfaces decorated with Polistof, Finish V 16 protects them from washing with common detergents and from abrasion.

FOR MAGIC LIGHT FINITURA K 100: it is to be applied over the top of new and old paint on smooth or rough supports, as long as they are properly fixed and not dusty before MAGIC LIGHT Finitura K 100

PREPARATION OF PRODUCT:

dilution: ready for use for the application on Polistof; to dilute at 100% for Artecó'1, ready to use for Magic Light Finitura K 100

APPLICATION:

system : by brush, by roller, by spray

STABILITY:

number of coats: 1 (with 2 coatings it verges on becoming glossy)
2 years

APPLICATION CYCLE:

FOR ARTECO'1 AND POLISTOF: apply by brush or by spray on Artecó'1 and Polistof surfaces already applied

FOR MAGIC LIGHT Finitura K 100: apply one coat of undiluted Finish V 16 using a brush or roller. After approximately 12 hours at 20°C, apply MAGIC LIGHT Finish K100

NOTE: The application and storage temperature has to be between +5°C and +35°C. Protect against frost. Tools must be carefully washed soon after use with soap and water

Technical Sheet n SC 00116 issued by the Quality Control Dpt.
Edition n 5 April 2014