

## METEORE 10

### Technical Sheet

**NAME:**

**METEORE 10**

**TYPE:**

A natural, water-based textured coating for interiors, ideal for reproducing the effect of cement in all its varieties

**USE:**

water based decoration paint for indoor use

**TECHNICAL DATA**

**specific weight:**

1.710 ± 30 gr/LT at 20°C

**viscosity:**

== =

**yield :**

1 – 1,5 m<sup>2</sup>/LT one coating on a smooth surface  
(it may vary according to the roughness, porosity and surface absorption and to the method of application )

2 – 2,5 m<sup>2</sup>/LT two coatings on a smooth surface  
(it may vary according to the roughness, porosity and surface absorption and to the method of application )

**aesthetic effect:**

satined textured product for a cement effect

**colours:**

colours from the catalogue

**packaging:**

LT. 1 - LT. 4-LT.12-

**on the surface:**

3-4 hours at 20°C

**overpainting :**

24 hours at 20°C

**below the painting:**

28 hours at 20°C

**DRYING TIME:**

**CHARACTERISTICS AND RESISTANCE:**

It hardens completely after 28 days, depending on temperature.

Once the product has hardened completely, a breathable film develops which offers good resistance to knocks and normal abrasion.

**METEORE 10 CEMENT EFFECT**

Reaction to Fire UNI EN 13501-1: **Class A1 (NON FLAMMABLE)**

Make sure that the surface is stable and remove any impurities. Eliminate any old flaky or crumbling paint and wash with an appropriate soap. Then plaster the surface where necessary and apply a fixative after the plaster has dried. Apply PRIMER 1200 with a felt roller, brush or spray. After 6 hours at 20°C, apply METEORE 10 and finish with C100 Over

**dilution:**

ready to use except for Effect Scored Cement which is to be diluted with water

**system:**

Stainless steel trowel , brush and roller

**coats:**

1

**PREPARATION OF THE PRODUCT:**

**APPLICATION:**

**APPLICATION CYCLE**

Apply METEORE 10 with a PV 43 stainless steel plastering trowel and finish while still wet with the tools required for the effect you wish to obtain.

Allow to dry for 24 hours at 20°C, then decorate with C100 OVER finish.

To highlight joints and give an effect which reflects the textures of cement casting forms, use VALPAIN PIXEL PENS, then finish with C100 OVER finish Once the coat of C100 OVER has dried, you can apply the indelible PIXEL PEN again, to emphasize the joints if you wish to do so.

METEORE 10 can be finished with a variety of effects.

**1) Compact cement.**

**Dilution:** to obtain this finish, do not dilute METEORE 10 or C100 OVER.

**Coverage:** METEORE 10, around 1 l per 1 - 1.5 squ.m., one coat over a smooth surface; C100 OVER, around 1 l per 4 - 5 squ.m., one coat.

## 2) Large cement.

**Dilution:** to obtain this finish, do not dilute METEORE 10 or C100 OVER.

**Coverage:** METEORE 10, around 1 l per 1 - 1.5 squ.m., one coat over a smooth surface; C100 OVER, around 1 l per 4 - 5 squ.m., one coat

**3) Slim cement. Dilution:** to obtain this finish, do not dilute METEORE 10; C100 OVER should be diluted 10% with water. **Coverage:** METEORE 10, around 1 l per 1 - 1.5 squ.m., one coat over a smooth surface; C100 OVER, around 1 l per 4 - 5 squ.m., one coat.

## 4) Ground cement.

**Dilution:** to obtain this finish, do not dilute METEORE 10 or C100 OVER.

**Coverage:** METEORE 10, around 1 l per 1 - 1.5 squ.m., one coat over a smooth surface; C100 OVER, around 1 l per 4 - 5 squ.m., one coat.

## 5) Scored cement.

**Dilution:** to obtain this finish, dilute METEORE 10 with 100 ml water per litre; C100 OVER should be diluted 10% with water. **Coverage:** METEORE 10, around 1 l per 2 - 2.5 squ.m., one coat over a smooth surface; C100 OVER, around 1 l per 2.5 - 3 squ.m., one coat.

**6) Marbling Effect:** Apply METEORE 10 to the entire wall, with the PV 44 stainless trowel. Next, while the product is still wet, run the PV 105 brush over the surface to create irregular, undulating grooves running obliquely from top to bottom and vice versa.

After 30 - 40 minutes at 20°C, spray the wall with water, again in strips, using the PV 106 spray. This will make it easier to smooth on METEORE 10 with the PV 44 stainless trowel.

After 24 hours at 20°C, decorate with a compact sponge, using SABULADOR SOFT finish. The first two coats should cover fully, leaving 4 hours at 20°C between each coat.

The next coat of SABULADOR SOFT should be applied, once again covering the entire surface, but then removed using the sponge after it has been rinsed in water and thoroughly squeezed.

The colour should be removed by swiping once or more times to create the nuances you like on the smoothest part of the surface. Similarly, the marbled effect is created by leaving different shades of colour in the notched veins.

If a fourth coat is to be applied, i.e. the third colour of SABULADOR SOFT, it should be applied in all of the notched veins, or around them, creating nuances using the sponge after it has been rinsed in water and thoroughly squeezed.

**N.B.: Before proceeding, please watch the video tutorial for the effect you wish to obtain**

**Application temperature:** between +10°C and +30°C.

**Storage:** make sure that the tin is tightly closed, even after use, and store at a temperature between +10°C and +30°

**Shelf life:** approximately 1 year, if well sealed and never opened

## NOTES:

Mix carefully the product before use. Wash the tools soon after use with water and soap.

Technical Sheet n° SC 00261 issued by the Control Responsible Department

Edition n° 4

February 2018

page 2 of 2