

SC 00219

PRIMER 900

Technical Sheet

NAME:

TYPE:

USE:

COMPOSITION:

CHARACTERISTICS:

PRIMER 900

water-based primer

grey water-based primer for indoor easy to apply.

special resins and charges allowing breath-

specific weight: 1.500 ± 30 gr/LT. at 20°C

yield: 14 - 15 m²/LT. for a coating (it may vary according to the roughness, surface absorption and application methods)

stability: 24 months, stock between +5°C and +30°C

colours: grey

packaging: LT. 0,500 - LT. 1

on the surface 2 hours at 20°C

overpainting : 4 - 6 hours at 20°C

in depth: 24 hours at 20°C

DRYING:

CHARACTERISTICS AND RESISTANCE:

grey water-based primer necessary to get the decorative effects of Klondike both indoor and outdoor. Primer 900 is easy to apply and it is characterised by a good covering, resistance and washability. It can be applied on several surfaces as cement, plaster, plaster of Paris, plasterboard, wood and iron and even on surfaces that have already been already painted (provided that the existing coat is not peeling).

dilution: ready to use

PREPARATION OF THE PRODUCTS:

APPLICATION:

system: by brush-by roller-by spray

number of coatings: 1 - 2 or more to cover

PREPARATION OF THE SURFACE:

Old walls. Remove old non-adhering and peeling paint and wash using water and a suitable soap product. Next, apply a fixative suited to the type of surface. When the fixative is completely dry, apply a coat of PRIMER 900 and, after 6 hours at 20°C, proceed with the application of KLONDIKE. **New walls.** Clean (and if necessary, fill) the surface you wish to paint. Once it is dry, sand the surface and apply a coat of suitable fixative. When the fixative is completely dry, apply a coat of PRIMER 900 and, after 6 hours at 20°C, proceed with the application of KLONDIKE. **Wood, glass, light alloys and painted iron.** Remove all grease from the surface and sand well, so that it is smooth and clean. Apply a coat of primer which is suited to that particular type of surface, then apply a coat of PRIMER 900. After 6 hours at 20°C, proceed with the application of KLONDIKE. **New iron (not treated).** Remove all grease and any layers of rust from the surface and apply one coat (or more) of a suitable anti-rust treatment. When this is completely dry, apply a coat of PRIMER 900 and, after 6 hours at 20°C, proceed with the application of KLONDIKE.

page 1 of 2



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC 00219

NOTES:

Temperature of application must be between +5°C and +30°C. Wash the tools soon after use with water and soap.

Technical Sheet n° SC 00219 issued by the Responsible Quality Control:

Edition n° 2

July 2012

page 2 of 2