

ANTICANDO 600

Technical Sheet

NAME:

ANTICANDO 600

TYPE:

thick coating water-based product which yields special antique effects.

USE:

Decoration of indoor plaster after the standard masonry wall preparations.

CHARACTERISTICS:

specific weight: 1.410 ± 30 gr/LT. at 25°C

viscosity: 16400+ 2000 cps

yield: 0,7 – 0,8 m²/LT (it may vary according to the roughness, porosity and surface absorption and to the method of application)

aesthetic effect: mat

colours: colours shown in the catalogue achievable using COLORI'

packaging: LT. 4 - LT. 12

on the surface: 1 hour at 20°C

overpainting: 8 - 10 hours at 20°C

below the surface: 24 hours at 20°C

sand 24 hours at 20°C

DRYING TIME:

CHARACTERISTICS AND RESISTANCE:

ANTICANDO 600 is made using acrylic resins and natural fillers. After application, the decorated surface remains breathable, washable and may be painted over. ANTICANDO 600 is easily applied to various types of surface, such as cement, plaster, plaster of Paris, plasterboard, wood and iron after suitable treatment has been applied.

PREPARATION OF THE SURFACE:

Old walls. Remove old non-adhering and peeling paint from the support and wash using water and a suitable soap product.

Next, apply a coat of PRIMERT 400 diluted 50% with water to act as a fixative. After approximately 4 hours at 20°C, apply a second brushed coat of PRIMER 400 diluted 20 - 30% with water. If, however, the surfaces are clean and not peeling, apply a coat of PRIMER 400 diluted 20 - 30% with water.

After 4 hours at 20°C, proceed with the application of ANTICANDO 600

PREPARATION OF THE PRODUCT :

dilution: ANTICANDO 600 is ready to use (it can be diluted with water to get the other decorative effects)

APPLICATION:

system: brush or spatula

coats: 1 or more

APPLICATION CYCLE:

ANTICANDO 600 is ready to use and should be mixed well. The special PV 77 plastic spatula or the plastic trowel PV 90 or PV 91 or a stainless steel trowel should be used to apply the product directly to both new and old sound surfaces which are free from dust, even if they have already been painted. An uneven layer should be spread over the entire surface, leaving visible irregular and raised strokes which are close together. After 8 hours at 20°C, when ANTICANDO 600 has dried properly, proceed with the application of non-coloured FINIX 80.

Page 2 of 2

SC 00198

After approximately 6-8 hours at 20°C, apply a second coat of coloured FINIX 80. On both coatings use a small quantity of products with irregular brush strokes in all directions. Next, while the FINIX 80 is still wet and using the PV 77 spatula, work the product with criss-crossed spatula strokes, exerting a strong pressure, on the surface.

N.B: ANTICANDO 600 becomes washable with water and common detergents after 15 days from application.

Storage: make sure the tin is tightly closed, even after use, at a temperature no lower than +5°C and no higher than +30°C.

Stability: approximately 2 years in well closed never opened tin

WARNING: ANTICANDO 600 IS A PRODUCT WHICH IS PARTICULARLY SENSITIVE TO THE TECHNIQUE OF THE PERSON APPLYING IT. IT IS THEREFORE ADVISABLE THAT ALL THE WORK IS PERFORMED BY THE SAME PERSON, IN ORDER TO AVOID DIFFERENCES IN THE EFFECT AND COLOUR ACHIEVED.

Note: mix well before using .Wash tools soon after use with water

**Technical Sheet n° SC 00198 issued by the Control Quality Department
 Edition n° 2 November 2015**

Page 2 of 2