



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC 00256

MAGIC LIGHT FINITURA K 110

Technical Scheet

NAME:

MAGIC LIGHT FINITURA K 110

TYPE:

Multicolor water –based luminescent finish in darkness and fluorescent in wood-violet light

USE:

Indoor decorations.

CHARACTERISTICS:

specific weight : 1.010 ± 30 gr/LT at 25°C

viscosity: = = =

yield: 8-10 m²/LT one coating on smooth surfaces (it may vary according to the roughness, porosity and surface absorption and to the method of application)

aesthetic effect: Luminescent in darkness and fluorescent in wood violet light

colours: Light Blue- in darkness; green,white, red and yellow in wood violet light

packaginig: LT. 0,500- LT. 1

DRYING:

on the surface: 3-6 hours at 20°C

Over-painting:

below the surface: 24-36 hours at 20°C

CHARACTERISTICS AND RESISTENCE:

white water-based paint for indoor use that absorbs both natural and artificial light before returning it in complete darkness.

This is precisely why, by lighting a room decorated with MAGIC LIGHT finish K110 for 5 minutes, when the lights is then switched off, the treated walls will gradually light up again before stabilizing a few minutes later.

Luminescence may last from 5 to 7 hours, depending on the quantity of light absorbed and the intensity of the darkness, reducing gradually over this time. MAGIC LIGHT Finish K110 remains white matt and breathable. If MAGIC LIGHT Finish K110 is lighted up with wood Light (neon or violet lamp) it will change its colour from a light blue (in dark) to green, red, yellow and white.

PREPARATION OF THE SURFACE

The surface to decorate is to be white or in light colour. If the surface has already been painted, this is must be well adhering and not peeling. On the contrary remove all imperfections and not adhering paints and apply 2 coatings of Primer 400 After 8 hours at 20°C apply MAGIC LIGHT Finish K110

PREPARATION OF THE PRODUCT:
APPLICATION:

thinning: ready to use – mix well with a wood stick

system: Brush-roller-sea spoge and spray

number coating: 1 or more

page 1 of 2



VALPAINT S.p.A.
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384
E-mail: info@valpaint.it
C.F./P.IVA/R.I. di AN 01108220425
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

APPLICATION CYCLE: Magic Light Finish K 110 can be applied on new and old paints, smooth or rough surfaces but well adhering and not peeling using Brush PV 76 or Sea Sponge PV32 or a Sea Sponge Roller with big grains Alternatively use compressor with multispray gun with nozzles 2,5-3mm.

Storage: make sure the tin is tightly closed, even after use, and store at a temperature between +5°C and +30°C.

Shelf life: approximately 1 year, if well sealed and never opened

NOTES:

Mix well before using with a wooden stick or metallic one

Application temperature must be not inferior to +5°C and superior to +30°C. Wash the tools soon after use with water and soap.

Technical sheet n° SC 00256 issued by the Control Quality Manager:

Edition n°1

April 2015

page 2 of 2