

FINISH V 18 LUCIDO

Technical Sheet

NAME:

FINISH V 18 LUCIDO

TYPE:

Interior natural transpiring paints

USE

Interior glossy transparent acrylic protection. Formulated and tested to protect Meteore 10 and C 100 Over or Sabulador Soft on the basis of the effect to create .

TECHNICAL DATA:

specific weight: 1.000 ± 30 gr/LT. at 25°C

viscosity: 400 cps

yield: 12 -15 m²/LT. one coating on a smooth surface (it may vary according to the roughness, porosity and surface absorption and to the method of application)

aesthetic effect: mat

colours: transparent

packaging: LT. 1

on the surface: 1 hour at 20°C

below the surface: 24 hours at 20°C

DRYING TIME:

CHARACTERISTICS AND RESISTANCE:

To make the decorated surface even more water resistant, apply FINISH V 18 Lucido transparent protective coating using roller, brush or spray after leaving to dry for 24 hours at 20°C.

PREPARATION OF THE SURFACE:

== =

PREPARATION OF THE PRODUCT:

dilution: ready to use

catalization relation: = = =

pot life: = = =

APPLICATION:

system: Apply one or two coats of FINISH V 18 Lucido depending on the degree of water resistance you wish to obtain. Allow the first coat to dry for 4 hours at 20°C before applying the second.

number of coatings: 1-2)

Application temperature: between +10°C and +30°C.

Storage: make sure the tin is tightly closed, even after use, and stored at a temperature no lower than +10°C and no higher than +30°C.

Stability: approximately 1 year, if well sealed and never opened

NOTE:

Mix carefully the product before use. Wash tools using water and soap after use

Technical Sheet n° SC 00264 issued by the Control Quality Department:

Edition n° 2

October 2018