

ARTECO' 7 METAL

Technical Sheet

NAME:

ARTECO' 7 METAL

TYPE:

perlescent effects paints

USE:

water based paint for indoor use

TECHNICAL DATA

specific weight: 1.020 ± 30 gr/LT at 20°C

viscosity: = = =

yield : 8 - 10 m²/LT (it may vary according to the roughness, porosity and surface absorption and to the method of application)

aesthetic effect: satined and metallic

colours: colours from the catalogue

packaging: LT. 1 - LT. 2,5 -

on the surface: 3 - 4 hours at 20°C

overpainting : = = =

below the painting: 24 - 36 hours at 20°C

DRYING TIME:

CHARACTERISTICS AND RESISTANCE:

A pearlescent water-based paint for interiors, offering a striking aesthetic impact. Thanks to its constantly-changing mobile effects, ARTECO' 7 METAL changes colour depending on the position of the observer and the reflected light

ENVIROMENTAL PERFORMANCES

PERFORMANCES	STANDARD	VALUE	BRAND
EMISSION OF INDOOR POLLUTING SUBSTANCES	ISO 16000	TVOC < 1 mg/m ³ A+Class	
ABSENCE OF DANGEROUS SUBSTANCES	-	FREE	
FORMALDEHYDE ISSUE RATE, X	JIS AT 1902-3	X < 0.005 mg/m ² h F****	
VOC On products to use	DIRECTIVE 2004-42-CE	max 4,8 g/L (UE Limite 200 g/L) Cat. A/1	

PREPARATION OF THE SURFACE:

Apply on new or old walls provided they are in good condition and are not oily, dusty or damp. Otherwise, treat them adequately and apply a suitable fixative. Subsequently, apply one covering coat of PRIMER 1200 diluted 15 - 20% using a woolen roller or brush (or sprayer) with criss-cross strokes for improved coverage. After 6 hours at 20°C, proceed with the application of ARTECO' 7 METAL

PREPARATION OF THE PRODUCT :

dilution: ready to use

catalization relation: = = =

pot life: = = =

system: brush, plastic spatula

coats: 1 - 2

APPLICATION:

APPLICATION CYCLE:

To obtain the effects shown in the catalogue, PRIMER 1200 must be coloured with the relative amount of COLORI' colouring paste. Alternatively, the VALCLONE dispensing system can be used. Furthermore, to obtain the metallic nuances, ARTECO' 7 METAL must be supplemented with the L50 product available in 6 different shades.

Apply and work over gradually on a small surface (approx. 1 - 2 m²) using brush PV 76. Apply the paint in all directions, by alternating strokes from right to left and vice-versa and from top to bottom and vice-versa, so that the product can even out properly. After roughly 5 - 10 minutes at 20°C, work over the treated part again using brush PV 76 without paint and move the particles towards the uncovered zones with soft superficial brush strokes. Once the smooth part of the paint has dried, while the relief particles are still wet (after about 10 minutes) smoothen ARTECO' 7 METAL lightly using the PV 77 plastic spatula with alternating and criss-cross strokes.

NB: on very rough, pitted, etc. walls, apply ARTECO' 7 METAL using brush PV 76 only, without using the PV 77 plastic spatula.

Storage: make sure that the tin is tightly closed, even after use, and store at a temperature between +10°C and +30°C.

Shelf life: approximately 1 year, if well sealed and never opened

NOTES:

Application temperature must be between +5°C and +30°C. Wash the tools soon after use with water and soap.

Technical Sheet n° SC 00250 issued by the Control Responsible Department

Edition n° 2

June 2019